



**TEHNIČNA SPECIFIKACIJA PAPIRJA**  
**TECHNISCHE SPEZIFIKATION DES PAPIERS**  
**PAPER SPECIFICATION**  
 TS: 5.3.2019

# Rcopy standard plus FSC

multipurpose office paper for use in laser printers, inkjet printers and copiers.

Parameter	Enota Einheit Unit	Vrednost Zielwert Target	Odstopanje Toleranz Tolerance	Standard
<b>Gramatura</b> <b>Flachengewicht</b> <b>Grammage</b>	g/m <sup>2</sup>	80	± 4 %	ISO 536
<b>Debelina</b> <b>Dicke</b> <b>Thickness</b>	µm	104	± 4 %	ISO 534
<b>Gladkost Bekk</b> <b>Glatte Bekk</b> <b>Smoot. Bekk</b>	s	27	± 10	ISO 5627
<b>Absolutna vlaga</b> <b>Abs. Feuchte</b> <b>Abs. moisture</b>	%	4,1	± 0,5	ISO 287
<b>Belina</b> <b>Weissgrad Brightness</b> <b>R 457 nm</b>	%	109	± 1	ISO 2470
<b>Belina CIE</b> <b>Weissgrad CIE</b> <b>Whiteness CIE</b>		157	- 3%	ISO 11475
<b>Opaciteta</b> <b>Opazität</b> <b>Opacity</b>	%	92	MIN	ISO 2471
<b>Utržna odpornost</b> <b>Zugfestigkeit</b> <b>Tensile s.</b>	kN/m	MD 2,7 CD 1,3	MIN	ISO 1924-2
<b>Togost Taber</b> <b>Steifigkeit Taber</b> <b>Stiffness-Taber</b>	mNm	MD 0,20 CD 0,10		TAPPI 489
<b>Hrapavost Bendsten</b> <b>Roughness</b> <b>Roughness</b>	ml/min	150	± 50	ISO 8791-2

Paper is produced from ECF pulp, and in accordance with ISO 9706 standard and standard EN 12281.